

Technical Data Sheet

Ultrasint® PA11 GB30

Technical Data Sheet for Ultrasint® PA11 GB30

Version No.: 1.1, revised 04/2021

General information

Components

Glass bead filled Polyamide 11 powder for Laser Sintering

Product Description

Ultrasint® PA11 GB30, a bio-based material (castor oil), is a functionally optimized PA11 with increased rigidity. Parts made of this material show a higher stiffness compared to unfilled PA11 maintaining a good balance regarding strength, stiffness and impact resistance. Typical applications are in environments where a high rigidity is required and/or where exposure to special surroundings (e.g. chemical, detergents, oil) may occur. Due to its high ductility, it does not splinter in most crash situations. Ultrasint® PA11 GB30 is processable on most common LS printers. Parameters for printing will be provided..

Typical applications are:

- Housings and covers
- Thermally loaded parts (i.e. close to the auto engine compartment)
- Splinter-proof jigs & fixtures
- Durable gears and bearings

Delivery form & warehousing

Ultrasint® PA11 GB30 should be stored at 15 – 25°C in its originally sealed package in a clean and dry environment.

Product safety

Mandatory and recommended industrial hygiene procedures and the relevant industrial safety precautions must be followed whenever this product is being handled and processed. Product is sensitive to humid environment conditions. For additional information please consult the corresponding material safety data sheets.

For your information

Ultrasint® PA11 GB30 comes in natural color. Electrical properties (e.g. volume resistivity, surface resistivity), chemical properties (e.g. resistance against particular substances) and tolerance for solvents are available upon request. Generally, these properties correspond to publicly available data on polyamides.

Notice

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

The safety data given in this publication is for information purposes only and does not constitute a legally binding Material Safety Data Sheet (MSDS). The relevant MSDS can be obtained upon request from your supplier or you may contact Forward AM directly at sales@basf-3dps.com.

Technical Data Sheet for Ultrasint® PA11 GB30

Version No.: 1.1, revised 04/2021

General Properties	Test Method	Typical Values
Bulk Density / kg/m ³	DIN EN ISO 60	700
Printed Part Density / kg/m ³	DIN EN ISO 1183-1	1240
Mean particle size d50 / μm	Laser Diffraction	40-50
Melting Temperature / °C	ISO 11357 (10 K/min)	203
Crystallization Temperature / °C	ISO 11357 (10 K/min)	160
Melt Volume Flow Rate / cm ³ /10min	ISO 1133 (220 °C, 2.16 kg)	10

Thermal Properties	Test Method	Typical Values ¹
HDT/A (1.8 MPa) / °C	ISO 75-2	87
HDT/B (0.45 MPa) / °C	ISO 75-2	176
Vicat/A (10 N) / °C	ISO 306	192
Vicat/B (50 N) / °C	ISO 306	171

Mechanical Properties	Test Method	Typical Values X-direction		Typical Values Z-direction	
		Dry ¹	Cond. ²	Dry ¹	Cond. ²
Tensile Strength / MPa	ISO 527-2 (23°C)	47	33	45	32
Tensile Modulus / MPa	ISO 527-2 (23°C)	2600	1200	2500	1200
Tensile Elongation at break / %	ISO 527-2 (23°C)	7	66	4	34
Tensile Strength / MPa	ISO 527-2 (80°C)	20	16	19	16
Tensile Modulus / MPa	ISO 527-2 (80°C)	550	300	550	300
Tensile Elongation at break / %	ISO 527-2 (80°C)	> 50	> 50	> 50	> 50
Flexural Modulus / MPa	DIN EN ISO 178	2550	1450	2450	1400
Charpy Impact Strength (notched) / kJ/m ²	ISO 179-1	6.3	13	5.7	10
Charpy Impact Strength (unnotched) / kJ/m ²	ISO 179-1	40	166	25	63
Izod Impact Strength (notched) / kJ/m ²	ISO 180	6.8	16	5.9	11
Izod Impact Strength (unnotched) / kJ/m ²	ISO 180	32	no break	20	51

 Detailed material data and support for FEA simulations available on request (sales@basf-3dps.com).

1) Measured after drying 14 days at 80°C / vacuum. Water content is about 0.08% acc. to DIN EN ISO 15512

2) Measured after conditioning 14 days at 70°C / 62% r.h. Water content is about 0.8% acc. to DIN EN ISO 15512

All values measured with virgin material.